



Technical Data Sheet

Fiberglass Mesh WMZ-120C



Technical Specifications

No.	Characterizations	Unit	Specification	Acceptance Criteria	Test Method
1	Type Glass	-	C-glass	-	-
2	Color	-	White	-	-
3	Mesh Size	mm	5x5 / 4x6	≥ 5	-
4	Length	M	50	-	-
5	Width	cm	20-25-33-40-50-60-100 (Up to Customer Order)	-	-
6	Mass per Unit Area	gr/m ²	≥ 120	≥ 100	ISO 3374
7	Breaking Strength (Before Alkali)	N/50 mm	≥ 1600	-	ASTM E 2098
		MPa	≥ 1280	≥ 1000	
8	Breaking Strength (After Alkali)	N/50 mm	≥ 1350	-	ASTM E 2098
		MPa	≥ 1080	≥ 1000	
9	Alkali Resistance (28-Day Test)	%	80	-	-

Application

C-glass Fiberglass WallMesh is a woven product made from glass fibers coated with alkali-resistant acrylic resins, designed for industrial and construction applications. With reliable resistance to alkali and corrosion, this mesh is ideal for reinforcing non-structural components in construction projects. Specifically engineered for cementitious environments it plays a crucial role as a primary component of Fabric-Reinforced Cementitious Matrix (FRCM) composites. These composites are widely used for strengthening and retrofitting concrete and masonry structures. The mesh ensures durability and long-term performance by maintaining its integrity in the harsh alkaline conditions of cement-based systems, making it an indispensable solution for advanced reinforcement applications. Moreover, it is also suitable for gypsum-based environments

Advantages

- High alkali and corrosion resistance for long-term durability
- Coated with alkali-resistant acrylic resins for chemical stability in cement environments.
- Strong adhesion to cement for effective reinforcement.
- Key component of Fabric-Reinforced Cementitious Matrix (FRCM) composites.
- Lightweight, easy to handle, and install.
- Ideal for industrial and construction applications.

Storage

The glass-fiber fabric should be stored in its original packaging in a dry environment. To ensure optimal preservation, we recommend protecting the packaging from direct sunlight. The ideal storage temperature ranges from -10°C to 50°C, with a recommended relative humidity of up to 50%.

Packaging

- 50 m² Cartons

Padidar Bon Novin Mehr

Address: Tehran, Saadat Abad, Darya Blvd., Sharifi Blvd.,

Tohid 2nd St., No. 55.

Tel: 021-8856 3504 - 021-8856 7318

www.wallmesh.ir ✉ Info@wallmesh.ir 📷 wallmesh